

NEW

EOLO PU EST ASW



PERMANENT ANTISTATIC TPU WALL
 $R < 10^9 \text{ Ohm/m}$



IPL

www.ipl.it

NEW

EOLO PU EST ASW



+80°C
-40°C

ASW

Transparent **ester based TPU** hose, reinforced with a grey anti-shock **rigid PVC spiral**. The special TPU formulation makes the hose wall **permanent antistatic** $R < 10^9$ Ohm/m, as it enables a continuous dissipation of electrostatic charges, as well as an optimization of flow properties, with an easier detachment of the media conveyed from the wall.

Excellent resistance to abrasion and torsion.

Wall thickness from 0,4 to 0,8 mm

Applications: suction of powders, granulates, chips and abrasive solids

Part number	Ø ins.	Min wall thick	Max wall thick	Weight	Vac.	Bending R.	Rollenl.	Vol.
	mm	mm	mm	g/m	m H ₂ O	mm	m	m ³
OU 86 013.0 000.0	13*	0,4	2,8	80	2,5	20	20	0,020
OU 86 016.0 000.0	16*	0,4	2,8	90	2,5	25	20	0,023
OU 86 019.1 000.0	19,1*	0,4	2,8	110	2,5	25	20	0,027
OU 86 020.0 000.0	20	0,4	2,8	110	2,5	25	20	0,028
OU 86 025.0 000.0	25	0,4	2,8	140	2,5	30	20	0,035
OU 86 030.0 000.0	30	0,4	2,8	170	2,5	35	20	0,068
OU 86 032.0 000.0	31,8	0,4	2,8	180	2	35	20	0,072
OU 86 035.0 000.0	35	0,5	3,0	200	2	45	20	0,079
OU 86 038.0 000.0	38,1	0,5	3,0	220	2	50	20	0,085
OU 86 040.0 000.0	40	0,5	3,0	230	2	60	20	0,088
OU 86 045.0 000.0	45	0,5	3,1	270	2	65	20	0,098
OU 86 052.0 000.0	50,8	0,5	3,4	330	2	70	20	0,111
OU 86 055.0 000.0	55	0,5	3,6	400	2	75	20	0,119
OU 86 060.0 000.0	60	0,5	3,8	470	1,6	80	20	0,130
OU 86 063.0 000.0	63,5	0,5	3,8	490	1,6	80	20	0,182
OU 86 065.0 000.0	65	0,5	3,8	510	1,6	90	20	0,186
OU 86 070.0 000.0	70	0,6	4,2	560	1,6	95	30	0,339
OU 86 076.0 000.0	76,2	0,6	4,2	610	1,6	100	30	0,365
OU 86 080.0 000.0	80	0,6	4,5	650	1,6	110	30	0,384
OU 86 090.0 000.0	90	0,6	4,6	750	1,4	125	30	0,429
OU 86 100.0 000.0	100	0,6	4,6	770	1,3	140	30	0,629
OU 86 102.0 000.0	102	0,6	4,6	780	1,3	140	30	0,641
OU 86 110.0 000.0	110	0,6	5,0	910	1,2	150	30	0,691
OU 86 120.0 000.0	120	0,6	5,3	1090	1	160	30	0,752
OU 86 127.0 000.0	127	0,6	5,3	1150	1	170	30	0,991
OU 86 130.0 000.0	130	0,7	5,6	1330	0,9	170	20	0,610
OU 86 140.0 000.0	140	0,7	5,6	1420	0,9	180	20	0,871
OU 86 150.0 000.0	151,5	0,7	5,9	1560	0,8	200	20	0,941
OU 86 152.0 000.0	152,4	0,7	5,9	1570	0,8	200	20	0,946
OU 86 160.0 000.0	160	0,7	7,1	1910	0,7	220	20	1,003
OU 86 180.0 000.0	180	0,7	7,1	2140	0,4	250	20	1,119
OU 86 200.0 000.0	200	0,7	7,2	2240	0,4	260	20	1,647
OU 86 203.0 000.0	203	0,7	7,2	2270	0,4	260	20	1,670
OU 86 250.0 000.0	250	0,8	8,0	3390	0,4	300	10	1,362
OU 86 300.0 000.0	300	0,8	8,2	4220	0,3	350	10	1,620

*Available on request and for agreed quantities



IPL

www.ipl.it

I dati riportati sono stati misurati a 23°C con 50% di umidità

IPL si riserva il diritto di modificare le informazioni ivi contenute e/o sospendere qualsiasi prodotto senza preavviso