


SPIRALPRESS OIL (Cod. SQ)



Tubo in speciale formulazione PVC-NBR, con spirale in PVC rigido antiurto e rinforzo tessile in poliestere. La sua struttura con spirale a vista consente di ridurre l'attrito durante lo scorrimento del tubo sul suolo. Il tubo può essere reso conduttivo ($R < 10^2$ Ohm/m) mettendo a terra il filo di rame posto sotto la spirale in PVC. Più leggero e flessibile rispetto ai convenzionali tubi in gomma. Molto resistente ad olii e lubrificanti.

• Ottima soluzione per aspirazione e mandata di petrolio e benzina con concentrazione aromatica fino al 50%. Spiralina disponibile su richiesta

Special black NBR-PVC tank drop hose, reinforced with an anti-shock rigid PVC spiral and Polyester yarn; exposed spiral for easy handling and dragging. The hose is conductive ($R < 10^2$ Ohm/m) by earthing the copper wire under the PVC spiral. Lighter and more flexible than conventional rubber hoses. It's very resistant to oils and lubricants.



• Excellent solution for suction and discharge of petroleum and gasoline with an aromatic content up to 50%. Banded coil available on request.



Speciale formulazione PVC-NBR / Special PVC/NBR formulation

Rinforzo tessile / Textile reinforcement

Spirale in PVC rigido antiurto / Anti-shock rigid PVC spiral



Spiralina disponibile (Cod. SC WT)
Banding coil available (Code SC WT)

Scheda tecnica / Technical data

Codice	Ø Int.	Ø Est.	Spess. Min.	Spess. Max	Peso	P.E.	Depr.	R. Curvatura	Lg. Rotolo	Vol.	Lg. Spiralina
Code	Ø Int.	Ø Out.	Min wall th.	Max wall th.	Weight	W.P.	Vac.	Bending	Coil lgth.	Vol.	Banding lgth.
	mm/inch	mm	mm	mm	g/m	[bar]	m H ₂ O	mm	m	m ³	mm
SQ010508000000	50,8/2"	66,6	3,2	7,9	1150	7	9,5	200	30	0,288	180
SQ010760000000	76,2/3"	96,2	3,7	10	1960	6	9	260	30	0,416	225
SQ011020000000	101,6/4"	123,0	3,7	10,7	2730	6	9	360	30	0,945	240
*Disponibile su richiesta, per quantitativi da concordare con l'ufficio vendite / *Available on request, contact our sales office for more info and quantities											
I dati tecnici qui riportati sono stati misurati a 23°C e al 50% di umidità / The technical data here reported were measured at 23°C with 50% humidity											